

A1070P

化学成分 (%)								
Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Al
0.20以下	0.25以下	0.04以下	0.03以下	0.03以下	—	0.04以下	0.03以下	99.7以上

母材		調質	板厚公差(mm)
板厚(mm)	幅 x 長さ(mm)		
2	1525x3050	H14	お問合せ
3	1500x5000	H112	
4	1500x6200	H112	±0.35
5	1500x6200	H112	±0.45
6	1500x6200	H112	±0.55
8	1500x6200	H112	±0.65
10	1500x6200	H112	±0.75
12	1500x6200	H112	
15	1500x5000	H112	±0.80
16	1500x5000	H112	
20	1500x5000	H112	±0.90
25	1500x5000	H112	±1.00
30	1500x5000	H112	
35	1500x5000	H112	±1.10
40	1500x5000	H112	±1.30
50	1500x5000	H112	±1.90
60	1500x5000	H112	
70	1500x5000	H112	±2.80
80	1500x5000	H112	
90	1500x5000	H112	

機械的性質		
引張強さ(N/mm ²)	耐力(N/mm ²)	延び(%)
—	—	—
—	—	—
75以上	35以上	10以上
70以上		
60以上	25以上	16以上
55以上	20以上	22以上
—	—	—